



DuPont Electronic Materials

Flexible Circuit Materials

# Pyralux® FR™ Sheet Adhesive

## Flexible Composites

### Description

Pyralux® FR™ sheet adhesive is a proprietary, flame-retardant, B-staged modified acrylic adhesive. Sheet adhesive is used primarily to bond flexible inner layers or rigid cap layers in multilayers. It can also be used to bond flexible circuits to rigid boards during the fabrication of rigid-flex circuits, as well as to bond stiffeners and heat sinks.

(76 mm) cores. Narrower widths or cut sheets are also available by special order.

### Construction

Pyralux® FR sheet adhesive is coated on release paper and is available in a variety of adhesive thicknesses; see **Table 1**.

The product code must be used when ordering sheet adhesive from DuPont.

### Typical Data

Each manufactured lot of sheet adhesive is certified to IPC specifications and tested according to IPC Test Method TM-650. See **Table 2**.

**Table 1**  
Sheet Adhesive Product Codes

Product Code	Adhesive mil (µm)	IPC Certification*
FR0100	1 (25)	Yes
FR0200	2 (51)	Yes
FR0300	3 (76)	Yes
FR0400	4 (102)	Yes
FR1500	1/2 (13)	Yes

\*Certified to IPC-232C/18: "Flexible Adhesive Bonding Film (Acrylic)"

### Packaging

Sheet adhesive is supplied on 24 in (610 mm) wide by 250 ft (76 m) long rolls, on nominal 3 in

**Table 2**  
Pyralux® FR™ Sheet Adhesive Properties

Property	Typical Sheet Adhesive Value	Test Method
Flammability*	VTM-0	UL94
Peel Strength†	—	IPC-TM-650, No. 2.4.9
After lamination	1.6 N/mm (9 lb/in)	Method B
After soldering	1.6 N/mm (9 lb/in)	Method D
Solder Float Resistance 10 sec at 288°C (550°F)	Pass	IPC-TM-650, No. 2.4.13 Method B
Adhesive Flow, µm/µm (mil/mil)	4.0	IPC-TM-650, No. 2.3.17.1
Thickness Tolerance	±10%	IPC-TM-650, No. 4.6.2
Dielectric Constant (at 1 MHz)	3.5	IPC-TM-650, No. 2.5.5.3
Dissipation Factor (at 1 MHz)	0.02	IPC-TM-650, No. 2.5.5.3
Dielectric Strength	118 kV/mm (3000 V/mil)	ASTM D-149
Insulation Resistance (at ambient)	10 <sup>6</sup> megohms	IPC-TM-650, No. 2.6.3.2
Volume Resistivity (at ambient)	10 <sup>9</sup> megohm-cm	ASTM D-257
Surface Resistance (at ambient)	10 <sup>7</sup> megohms	ASTM D-257

\* Pyralux® FR0200 and FR0300 meet UL 94 VTM-0 criteria.

† Laminating Conditions: 14 kg/cm<sup>2</sup> (200 psi), 182°C (360°F), 1 hour to treated side of 1 oz RA copper foil.

A Certificate of Compliance (COC) is available with every batch. Complete material and manufacturing records for each lot, with samples of finished laminate, are retained for reference purpose. The roll labels contain the lot number, DuPont order number, customer order number, IPC specification, customer specification, and customer part number; save these labels for reference in case of inquiries.

## Processing

Laminating conditions for Pyralux® flexible composites are typically in the following ranges:

Part Temperature: 182–199°C (360–390°F)

Pressure: 14–28 kg/cm<sup>2</sup> (200–400 psi)

Time: 1–2 hours, at temperature

Pyralux® FR™ can be processed like Pyralux® FR. Refer to publication “Pyralux® Flexible Composites Technical Manual” for further processing details.

## Storage

Pyralux® flexible composites will retain their original properties for a minimum of one year when stored in the original packaging at temperatures of 4–29°C (40–85°F) and below 70% humidity. The products do not need refrigeration and should not be frozen. Keep the material clean and well protected.

Sheet adhesive should not be automatically discarded if storage conditions have deviated from these limits. We recommend that material which has been stored outside these conditions be examined in a practical test run before being committed to production.

## Safe Handling

Pyralux® FR™ coverlay, sheet adhesive, and bond ply contain a B-staged adhesive. Since B-staged adhesive contains trace quantities (parts per million) of unreacted monomers, operators should take care to minimize contact.

Pyralux® FR™ copper-clad laminates contain fully cured (C-staged) adhesive.


Although DuPont is not aware of anyone developing contact dermatitis when using Pyralux® FR™ products, some individuals may be more sensitive than others. Anyone handling Pyralux® FR™ copper-clad laminates should wash their hands with soap before eating, smoking, or using restroom facilities. Gloves, finger cots, and finger pads should be changed daily. Clothes should be washed frequently.

The unreacted acrylic monomer in the adhesive may impart a mild odor when the release film or paper is removed. We recommend that areas where B-staged materials are used, as well as lay-up and lamination areas, be well ventilated with a fresh air supply.

Pyralux® adhesive is cured during lamination. The curing reaction does not produce any vapors, although impurities may volatilize. When drilling or routing parts made with Pyralux® FR™ flexible composites, provide adequate vacuum around the drill head to minimize worker exposure to adhesive dust.

Thin copper-clad laminates can have sharp metal edges. People handling these materials should be cautioned and provided with suitable gloves to prevent cuts.

Pyralux® FR™ flexible composites DO NOT contain polybrominated biphenyls (PBBs), polybrominated biphenyl oxides (PBBOs), or polybrominated diphenyl ethers (PBDEs).



DuPont Electronic Materials · 14 T.W. Alexander Drive · Research Triangle Park, NC 27709-4425

(800) 243-2143, Ext. 3637

Come visit us on the Internet at: <http://www.dupont.com/fcm>

The information given herein is based on data believed to be reliable, but the DuPont Company makes no warranties express or implied as to its accuracy and assumes no liability arising out of its use by others. This publication is not to be taken as a license to operate under, or recommendation to infringe, any patent.

**Caution:** Do not use in medical applications involving permanent implantation in the human body. For other medical applications, see “DuPont Medical Caution Statement,” H-50102.



DuPont Electronic Materials